

Data sheet: Septum for needle piercing. Item no. 900049.



Micro Port

Item no. 900049 (10,5mm)

Technical Specification:

Membrane:			900049
Type:			IIR/EPDM
Colour			Light Grey
Hardness	°Sha		40±5 (IRHD)
Tensile strength	MPa		10
Elongation at break	%		600
Density	g/cm ³		$1,07\pm0,03$
Range of temperature in dry atmospheric air °C			-40 - + 110°C
Compression set, DIN 53517, 24h/175°C %		Medium	
Wear resistance		N/A	
Tear resistance		Low (strength 10)	
Resistance to Weather and Ozone		Medium / good	
Resistance to Hydrolysis (water and steam)		N/A	
Resistance to Chemicals (acids/bases)		N/A	
Resistance to mineral	oil and gas		Limited
Air and gas density			N/A
Food safe			Yes (FDA*)
*FDA approved compound according to Code of Federal Regulations Title 21 - § 177.2600			

The MicroPort membrane can be pierced up to 20 times and can withstand 6 bar(g) maximum pressure. Please note with higher pressure each membrane can sustain fewer piercing.

